



| | |
|----------------------|--------------------------------|
| Ref. RC.ISO.28.M3838 | Covered grating, RC ISO28M3838 |
|----------------------|--------------------------------|

Gratings produced in compliance with standards ASTM D2583-07; ASTM D790-07e1; ASTM D638-08; ASTM G154-06; ISO 4589-2.

The quantity of fiber glass reinforcement is of 30% to 35% (by total weight).

Standard resin is isophthalic polyester with flame spread retardant → Rein IFR 25.

Flame spread rating ≤ 25 in compliance with standard ASTM E-84

All products have UV inhibitors and antioxidants.

| PROPERTIES | VALUES | |
|----------------------|-------------------------|--|
| H | 28,00 mm | |
| A | 38,00 mm | |
| B | 38,00 mm | |
| C | 30,00 mm | |
| D | 30,00 mm | |
| E | 6,30 mm | |
| F | 5,00 mm | |
| Weight (theoretical) | 18,00 Kg/m ² | |
| Open surface | 0,00 % | |

| SURFACE TYPE | AVAILABILITY |
|-------------------|-----------------|
| G - Grit (silica) | Usually stocked |
| L - Checkered | On demand |
| S - Smooth | On demand |