



Ref. RC.ISO.41.M3838	Covered grating, RC ISO41M3838
----------------------	--------------------------------

Gratings produced in compliance with standards ASTM D2583-07; ASTM D790-07e1; ASTM D638-08; ASTM G154-06; ISO 4589-2.

The quantity of fiber glass reinforcement is of 30% to 35% (by total weight).

Standard resin is isophthalic polyester with flame spread retardant – Rein IFR 25.

Flame spread rating  $\leq 25$  in compliance with standard ASTM E-84

All products have UV inhibitors and antioxidants.

PROPERTIES	VALUES	
H	41,00 mm	
A	38,00 mm	
B	38,00 mm	
C	30,00 mm	
D	30,00 mm	
E	7,00 mm	
F	5,00 mm	
Weight (theoretical)	25,00 Kg/m <sup>2</sup>	
Open surface	0,00 %	

SURFACE TYPE	AVAILABILITY
G – Grit (silica)	Usually stocked
L – Checkered	On demand
S – Smooth	On demand